


Zotefoams plc

Technical Information Sheet – TIS 09 (previously T13) Energy Absorption Capacity of Azote Foams



INTRODUCTION

The energy absorption characteristics of Plastazote foams are shown in the table for compressions at velocities of 100 mm/min.

Dynamic performance will be similar, with energy absorption capacity slightly enhanced. The data given is for the first compression on samples 100 x 100 x 30 mm.

Grade	Energy Absorbed J/cm ³						
	Compression						
	10%	20%	30%	40%	50%	60%	70%
Plastazote [®] LD24	0.002	0.006	0.012	0.019	0.029	0.043	0.064
Plastazote [®] LD33	0.003	0.008	0.015	0.024	0.036	0.052	0.078
Plastazote [®] LD45	0.005	0.013	0.022	0.034	0.048	0.067	0.095
Plastazote [®] LD60	0.011	0.026	0.042	0.061	0.083	0.123	0.149
Plastazote [®] LD70	0.010	0.028	0.046	0.067	0.092	0.111	0.168
Plastazote [®] HD30	0.011	0.025	0.039	0.056	0.075	0.098	0.129
Plastazote [®] HD60	0.035	0.085	0.134	0.185	0.243	0.312	0.403
Plastazote [®] HD80	0.047	0.124	0.202	0.281	0.366	0.468	0.601
Plastazote [®] HD115	0.060	0.168	0.275	0.383	0.501	0.641	0.821
Propozote [®] PPA30	0.009	0.020	0.033	0.047	0.064	0.085	0.113
Evazote [®] EV50	0.002	0.005	0.011	0.018	0.027	0.042	0.063

The stiffer and more dense the foam, the greater the energy absorbed.

ZOTEFOAMS MAKES NO WARRANTIES EXPRESS OR IMPLIED, EXCEPT TO THE EXTENT SET OUT IN THE CONDITIONS OF SALE, AND HEREBY SPECIFICALLY EXCLUDES ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ANY GOODS, MATERIALS OR PRODUCTS DESCRIBED HEREIN.

Zotefoams plc
675 Mitcham Road
Croydon
CR9 3AL
United Kingdom
Telephone: +44 (0) 20 8664 1600
Telefax: +44 (0) 20 8664 1616

Zotefoams Inc.
55 Precision Drive
Walton, Kentucky,
41094
USA
Telephone: +1 859 371 4046
Freephone: (800) 362-8358 (US Only)
Telefax: +1 859 371 4734



ISO 9001:2000
FM 01870



ISO 14001
EMS 36270

PLASTAZOTE[®], EVAZOTE[®], SUPAZOTE[®] and PROPOZOTE[®] are registered trade marks of Zotefoams plc.



August 2002