

Zotefoams plc

BULLETIN

ZOTEK N: Handling and Manufacturing Guidelines

Shipping:

- 1. ZOTEK N being of a base polyamide (nylon) polymer is hygroscopic in nature. It is good practice to control this characteristic and consider any effect through all handling and manufacturing processes. This document outlines key considerations.
- 2. ZOTEK N sheets are manufactured and prepared for despatch by Zotefoams PLC fully wrapped on a pallet in a typical pre-conditioned state.
- 3. Delivery and collection methods should ensure material is always in a covered vehicle and material is never subjected to outside elements, i.e. rain.
- 4. This is also true of customer's further subsequent fabricated shipments where care must be taken to ensure packaging and wrapping is adequate to avoid exposure to moisture or heat.

Storage:

- ZOTEK N should be stored inside at ambient conditions; ideally twenty three degrees Centigrade and 50% relative humidity where possible and should never be subjected to hot or moist environments.
- 2. It is also important to note that ZOTEK N "in fabrication" is always stored and processed in normal ambient factory environments to maintain the "as despatched" state of the product.

Processing:

- 1. For high heat processes such as thermoforming it is recommended that as for other materials suitable extraction methods are used.
- 2. Exposure to moisture is to be avoided; for example it is not recommended to subject ZOTEK N to water jet cutting for instance. Equally lengthy exposure to high heat sources during fabrication is also not recommended, i.e. close proximity to heaters or under hot lamps.
- 3. Post processing small dimensional variances can occur and care should be taken to assess this in regard to the correct processing blank and final geometric sizes or thickness requirements of your particular application. Dimensional validation after one hour, twenty four hours or after one week for instance will assist you in determining any effects along with suitable testing in application confirming the suitability of ZOTEK N to meet full customer requirements.
- 4. It is important to ensure that correct thermoforming temperatures are utilised for the particular grade of ZOTEK N being produced. Please contact us for further advice if necessary or refer to our fabrication guidelines.

Product Design:

 Final product application including tolerances required and usage environment should be discussed upon initial enquiry with either Zotefoams Technical or Sales representatives or Zotefoams distributor of product to ensure full customer satisfaction.

EXCLUSION OF LIABILITY:

United Kingdom

Any information contained in this document is, to the best of the knowledge and belief of Zotefoams plc and or Zotefoams Inc. (together herein referred to as ZOTEFOAMS), accurate. Any liability on the part of ZOTEFOAMS or any subsidiary or holding company of ZOTEFOAMS for any loss, damage, costs or expenses directly or indirectly arising out of the use of such information or the use, application, adaptation or processing of any goods, materials or products described herein is, save as provided in ZOTEFOAMS' conditions of sale ("Conditions of Sale"), hereby excluded to the fullest extent permitted by law.

Where ZOTEFOAMS' goods or materials are to be used in conjunction with other goods or materials, it is the responsibility of the user to obtain from the manufacturers or suppliers of the other goods or materials all technical data and other properties relating to those other goods or materials. Save as provided in the Conditions of Sale no liability can be accepted in respect of the use of ZOTEFOAMS' goods or materials in conjunction with any other goods or materials.

Where ZOTEFOAMS' goods or materials are likely to come into contact with foodstuffs or pharmaceuticals, whether directly or indirectly, or are likely to be used in the manufacture of toys, prior written confirmation of compliance with relevant legislative or regulatory standards for those applications may be requested from ZOTEFOAMS, if appropriate. Save as provided in the Conditions of Sale no liability can be accepted for any damage, loss or injury directly or indirectly arising out of any failure by the user to obtain such confirmation or to observe any recommendations given by or on behalf of ZOTEFOAMS.

ZOTEFOAMS MAKES NO WARRANTIES EXPRESS OR IMPLIED, EXCEPT TO THE EXTENT SET OUT IN THE CONDITIONS OF SALE, AND HEREBY SPECIFICALLY EXCLUDES ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ANY GOODS, MATERIALS OR PRODUCTS DESCRIBED HEREIN.

Plastazote[®], Evazote[®], Supazote[®] and ZOTEK[®] are registered trademarks of Zotefoams plc.

Zotefoams plc Zotefoams Inc.
675 Mitcham Road 55 Precision Drive
Croydon Walton, Kentucky,
CR9 3AL 41094

Telephone: +44 (0) 20 8664 1600 Telephone: +1 859 371 4046
Telefax: +44 (0) 20 8664 1616 Freephone: (800) 362-8358 (US Only)

Telefax: +1 859 371 4734

USA