

# Technical Information Sheet – TIS 17

## Static Dissipative Azote® Foams

### Introduction

Zotefoams have a range of conductive foams from the Azote® product ranges which are suitable for packaging and handling of devices that are sensitive to electrostatic discharges (ESD). This bulletin aims to give an overview of the properties and applications for the static dissipative (SD) grades. For general information on ESD protection please consult technical information sheet TIS 18 and for specific information on conductive products please consult technical information sheet TIS 16.

Two static dissipative foams are currently available from the Azote range, Plastazote® LD30SD and Plastazote® LD40SD. The materials are black and available in form of sheets.

Like all Zotefoams materials the SD grades are expanded using our unique nitrogen expansion process. This ensures that it is free of halocarbon or hydrocarbon blowing agents. It also shares the typical characteristics of our standard foams such as closed cell structure, isotropic physical properties, good performance as cushioning material, good chemical resistance.

### Advantages of Zotefoams static dissipative foam

The formulation used to produce Plastazote® LD30SD and Plastazote® LD40SD overcomes the problems typically associated with the production of a polyethylene foam suitable for packaging ESD sensitive equipment. The general approaches to modification of polyethylene foams include surface treatment with chemicals, chemical additives such as amides or amines and conductive fillers.

The surface treatment with e.g. aqueous salt solutions adds to the costs of the converter and is often unreliable as it can be rubbed or washed off and requires high humidity to function effectively.

Chemical additives like amines rely on migration of the additive to the surface of the material. While this method tends to give a more lasting effect than the surface treatment, leaching of some additives can cause deterioration of the electrical equipment the foam is meant to protect and increased surface resistivity due to loss of the additive. This method also requires (high) humidity to give a satisfactory performance.

Conductive fillers such as carbon black can be used to create permanent low resistivity however formulation of materials in the static dissipative range have proven difficult, as materials tend to be either conductive or insulative. This is due to the properties of carbon black which requires certain concentrations to create a conductive material.

As a result of extensive development Zotefoams is able to control the formulation of its Plastazote® LD30SD and Plastazote® LD40SD materials to give a truly static dissipative nitrogen blown crosslinked polyethylene foam.

## Applications

Together with the conductive foam grades (see technical information sheet TIS 16) the static dissipative foams provide a comprehensive range of materials for ESD control applications. Plastazote® LD30SD has good cushioning properties and can be used for packaging of materials where only limited conductivity is required. Plastazote® LD40SD has been developed to meet the higher density specifications required by the Ministry of Defence for static dissipative packaging material. Like the conductive Plastazote® grades it has good pin insertion and retention characteristics which enable a safe transport of IC devices.

## Compliance with Standards

The definitions of conductive foams vary slightly between the different standards. Below is a summary of the Standards that are concerned with ESD protection in packaging and the definition given for static dissipative materials in these standards. Surface resistivity is tested to ANSI/ESD STM 11.11-2015.

### General Standards:

ANSI/ESD S541-2003	Material with a volume resistance equal to or greater than $10^4 \Omega$ but less than $10^{11} \Omega$ or surface resistance equal to or greater than $10^4 \Omega$ but less than $10^{11} \Omega$
ANSI/ESD STM 11.11	Material with a surface resistance equal to or greater than $10^4 \Omega$ but less than $10^{11} \Omega$
JESD625-A	Material with a volume resistivity between $10^5 \Omega \cdot \text{cm}$ but less than $10^{11} \Omega \cdot \text{cm}$ or surface resistance between $10^5 \Omega$ and $10^{11} \Omega$

### Military Standards:

DStan 81-146	Material with a surface resistance of $10^5 \Omega$ to $10^9 \Omega$ and a density between $40 \text{ kg/m}^3$ and $50 \text{ kg/m}^3$ (Plastazote® LD40SD)
MIL-HDBK-263B	Material with a volume resistivity equal to or greater than $10^4 \Omega \cdot \text{cm}$ but less than $10^{11} \Omega \cdot \text{cm}$ or surface resistivity equal to or greater than $10^5 \Omega/\text{sq}$ but less than $10^{12} \Omega/\text{sq}$

The materials also meet the requirements for static dissipative flooring, work surfaces and other items given in standards by the ESD Association.

## EXCLUSION OF LIABILITY

Any information contained in this document is, to the best of the knowledge and belief of Zotefoams plc and of Zotefoams Inc. (together herein referred to as **ZOTEFOAMS**), accurate. Any liability on the part of **ZOTEFOAMS** or any subsidiary or holding company of **ZOTEFOAMS** for any loss, damage, costs or expenses directly or indirectly arising out of the use of such information or the use, application, adaptation or processing of any goods, materials or products described herein is, save as provided in **ZOTEFOAMS'** conditions of sale ("Conditions of Sale"), hereby excluded to the fullest extent permitted by law.

Where **ZOTEFOAMS'** goods or materials are to be used in conjunction with other goods or materials, it is the responsibility of the user to obtain from the manufacturers or suppliers of the other goods or materials all technical data and other properties relating to those other goods or materials. Save as provided in the Conditions of Sale no liability can be accepted in respect of the use of **ZOTEFOAMS'** goods or materials in conjunction with any other goods or materials.

Where **ZOTEFOAMS'** goods or materials are likely to come into contact with foodstuffs or pharmaceuticals, whether directly or indirectly, or are likely to be used in the manufacture of toys, prior written confirmation of compliance with relevant legislative or regulatory standards for those applications may be requested from **ZOTEFOAMS**, if appropriate. Save as provided in the Conditions of Sale no liability can be accepted for any damage, loss or injury directly or indirectly arising out of any failure by the user to obtain such confirmation or to observe any recommendations given by or on behalf of **ZOTEFOAMS**.

**ZOTEFOAMS MAKES NO WARRANTIES EXPRESS OR IMPLIED, EXCEPT TO THE EXTENT SET OUT IN THE CONDITIONS OF SALE, AND HEREBY SPECIFICALLY EXCLUDES ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ANY GOODS, MATERIALS OR PRODUCTS DESCRIBED HEREIN.**

### Zotefoams plc

675 Mitcham Road,  
Croydon,  
Surrey  
CR9 3AL  
United Kingdom  
Telephone: +44 (0) 20 8664 1600  
Telefax: +44 (0) 20 8664 1616  
[www.zotefoams.com](http://www.zotefoams.com)

### Zotefoams Inc

55 Precision Drive  
Walton  
Kentucky  
41094  
USA  
Telephone: +1 859 371  
Freephone: (800) 362-8358 (US Only)  
Telefax: +1 859 371 4734

Zotefoams plc Management systems are covered by the following:



**Quality**  
FM 01870



**Safety**  
OHS 52538



**Environment**  
EMS 36270