

# ZOTEK® F OSU SR

## High Performance Foams

**ZOTEK®**

### Product information

#### Typical values

ZOTEK® F OSU Semi-Rigid is a closed cell, foam of density 38 kg/m<sup>3</sup> made from poly vinylidene fluoride available in sheet form. The foam will thermoform into simple and complex shapes. This product information sheet provides typical values for the foam and does not constitute a specification.

Property	Test Standard	Units	Typical Value
<b>Apparent Density</b> Skin/Skin	BS EN ISO 7214:2012	kg/m <sup>3</sup> (pcf)	38 (2.4)
<b>Cell Size</b> (cell diameter)	Internal	mm (in)	0.27 (0.01)
<b>Compression Stress-Strain</b> 25% compression	BS EN ISO 7214:2012 1 <sup>st</sup> Compression	kPa (psi)	85 (12.3)
<b>Tensile Strength</b>	BS EN ISO 7214:2012	kPa (psi)	680 (98.6)
<b>Tensile Elongation</b>		%	120
<b>Compression Set</b> 50% comp. / 22hr / 23°C ½ hr recovery	BS EN ISO 7214:2012 25mm cell-cell	% set	
<b>Thermal conductivity</b> Mean temperature of 25 °C (77 °F) Mean temperature of 38 °C (100 °F)	ISO 8301	W/m.K (Btu in/ft <sup>2</sup> .hr.°F)	0.0356 (0.247) 0.0358 (0.248)
<b>Flammability</b> Heat Release Smoke Density Smoke Density Toxic Gas Emission	FAR/CS 25.853 (d) App F Pt IV FAR/CS 25.853 (d) App F Pt V ABD0031 para.7.3.2. ABD0031 para.7.4		Pass at 13mm (½") Pass at 25mm (1") Pass at 25mm (1") Pass at 25mm (1")
<b>Recommended maximum operating temperature*</b>	Internal	°C (°F)	140 (284)

\* Recommended maximum operating temperature

The maximum operating temperature shown is defined as the temperature which will typically cause a linear shrinkage of 5% after a 24hr exposure period, using sample dimensions of 100mm x 100mm x 25mm. This figure is provided for general guidance only. The actual level of shrinkage the foam will undergo at any temperature is dependent on several system variables such as, sample dimensions, cell size, loading conditions and exposure period.

# ZOTEK® F OSU SR

## High Performance Foams

ZOTEK®

### Exclusion of Liability

Any information contained in this document is, to the best of the knowledge and belief of Zotefoams plc and of Zotefoams Inc. (together herein referred to as ZOTEFOAMS), accurate. Any liability on the part of ZOTEFOAMS or any subsidiary or holding company of ZOTEFOAMS for any loss, damage, costs or expenses directly or indirectly arising out of the use of such information or the use, application, adaptation or processing of any goods, materials or products described herein is, save as provided in ZOTEFOAMS' conditions of sale ("Conditions of Sale"), hereby excluded to the fullest extent permitted by law. Where ZOTEFOAMS' goods or materials are to be used in conjunction with other goods or materials, it is the responsibility of the user to obtain from the manufacturers or suppliers of the other goods or materials all technical data and other properties relating to those other goods or materials. Save as provided in the Conditions of Sale no liability can be accepted in respect of the use of ZOTEFOAMS' goods or materials in conjunction with any other goods or materials.

Where ZOTEFOAMS' goods or materials are likely to come into contact with foodstuffs or pharmaceuticals, whether directly or indirectly, or are likely to be used in the manufacture of toys, prior written confirmation of compliance with relevant legislative or regulatory standards for those applications may be requested from ZOTEFOAMS, if appropriate. Save as provided in the Conditions of Sale no liability can be accepted for any damage, loss or injury directly or indirectly arising out of any failure by the user to obtain such confirmation or to observe any recommendations given by or on behalf of ZOTEFOAMS.

ZOTEFOAMS MAKES NO WARRANTIES EXPRESS OR IMPLIED, EXCEPT TO THE EXTENT SET OUT IN THE CONDITIONS OF SALE, AND HEREBY SPECIFICALLY EXCLUDES ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ANY GOODS, MATERIALS OR PRODUCTS DESCRIBED HEREIN.

Zotefoams plc Management systems are covered by the following:



**Quality**  
FM 01870  
ISO 9001 2015



**Safety**  
OHS 52538  
OHSAS 18001 2007



**Environment**  
EMS 36270  
ISO 14001 2015

#### ZOTEFOAMS plc

675 Mitcham Road  
Croydon  
Surrey  
CR9 3AL  
United Kingdom

Tel: +44 (0) 20 8664 1600  
Fax: +44 (0) 20 8664 1616  
Email: [info@zotefoams.com](mailto:info@zotefoams.com)

#### ZOTEFOAMS inc

55 Precision Drive  
Walton  
Kentucky  
41094  
USA

Tel: +1 859 371  
Freephone: (800) 362 8358 US only  
Fax: +1 859 371 4734

ZOTEK® is a registered trademark of Zotefoams plc. All rights reserved

Issue 0 Revision 0  
December 2019