

ZOTEK® F30

High Performance Foam

ZOTEK® high-performance technical foams are manufactured using Zotefoams’ unique autoclave technology. This process provides superior technical properties to satisfy the increasingly complex needs of high-tech manufacturers.

TYPICAL VALUES

The values provided represent data gathered from random samples of our production of the foam and should be considered as guidance for selecting a suitable grade for a given application. This does not constitute a specification.

PROPERTY	TEST STANDARD	UNITS	TYPICAL VALUE
Apparent Density Skin/Skin	ISO 7214:2012	kg/m ³ (pcf)	30 (1.9)
Cell Size (Cell Diameter)	Internal	mm (in)	0.27 (0.01)
Compression Stress-Strain 25% Compression	ISO 7214:2012	kPa (psi)	50 (7.25)
Tensile Strength	ISO 7214:2012	kPa (psi)	400 (58)
Tensile Elongation		%	190
Compression Set 50% Comp./22 Hour/23°C ½ Hour Recovery	ISO 1856:2018 Method C	% set	13
Thermal Conductivity (Mean Temperature) 25°C (77°F) 40°C (104°F) 80°C (176°F)	ISO 8301	W/m.K (Btu in/ft ² .hr.°F)	0.033 (0.226) 0.038 (0.266) 0.046 (0.316)
Recommended Maximum Operating Temperature*	Internal	°C (°F)	110 (230)

PROPERTY	TEST STANDARD	TYPICAL VALUE
Flammability		
Heat Release	FAR/CS 25.853 (d) App F Pt IV	Pass at 3, 13, & 25mm (1/8", 1/2" & 1")
Smoke Density	FAR/CS 25.853 (d) App F Pt V	Pass at 13mm (1/2")
Smoke Density	ABD0031 para.7.3.2.	Pass at 13mm (1/2")
Toxic Gas Emission	ABD0031 para.7.4	Pass at 13mm (1/2")
Radiant Heat Panel	FAR 25.856 (a) App F Pt VI	Pass at 3 & 25mm (1/8" & 1")
Vertical Burner (60 sec)	FAR/CS 25.853(a) App F Pt I(a), (1), (i)	Pass at 1.5, 13 & 25mm (1/16", 1/2" & 1")

*Recommended maximum operating temperature

The maximum operating temperature shown is defined as the temperature which will typically cause a linear shrinkage of 5% after a 24hr exposure period, using sample dimensions of 100mm x 100mm x 25mm. This figure is provided for general guidance only. The actual level of shrinkage the foam will undergo at any temperature is dependent on several system variables such as, sample dimensions, cell size, loading conditions and exposure period.

EXCLUSION OF LIABILITY

Any information contained in this document is, to the best of the knowledge and belief of Zotefoams UK, Zotefoams Poland and Zotefoams USA, (together herein referred to as ZOTEFOAMS), accurate. Any liability on the part of ZOTEFOAMS or any subsidiary or holding company of ZOTEFOAMS for any loss, damage, costs or expenses directly or indirectly arising out of the use of such information or the use, application, adaptation or processing of any goods, materials or products described herein is, save as provided in ZOTEFOAMS' conditions of sale ("Conditions of Sale"), hereby excluded to the fullest extent permitted by law.

Where ZOTEFOAMS' goods or materials are to be used in conjunction with other goods or materials, it is the responsibility of the user to obtain from the manufacturers or suppliers of the other goods or materials all technical data and other properties relating to those other goods or materials. Save as provided in the Conditions of Sale no liability can be accepted in respect of the use of ZOTEFOAMS' goods or materials in conjunction with any other goods or materials.

Where ZOTEFOAMS' goods or materials are likely to come into contact with foodstuffs or pharmaceuticals, whether directly or indirectly, or are likely to be used in the manufacture of toys, prior written confirmation of compliance with relevant legislative or regulatory standards for those applications may be requested from ZOTEFOAMS, if appropriate. Save as provided in the Conditions of Sale no liability can be accepted for any damage, loss or injury directly or indirectly arising out of any failure by the user to obtain such confirmation or to observe any recommendations given by or on behalf of ZOTEFOAMS.

ZOTEFOAMS MAKES NO WARRANTIES EXPRESS OR IMPLIED, EXCEPT TO THE EXTENT SET OUT IN THE CONDITIONS OF SALE, AND HEREBY SPECIFICALLY EXCLUDES ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ANY GOODS, MATERIALS OR PRODUCTS DESCRIBED HEREIN.

For details on Zotefoams Management Systems, please visit www.zotefoams.com

Zotefoams UK
675 Mitcham Road
Croydon, Surrey CR9 3AL
United Kingdom
Tel: +44 (0) 20 8664 1600
Email: hello@zotefoams.com

**Zotefoams Poland
SP z.o.o.**
Parkowa 26
49-318 Skarbimierz,
Osiedle

Zotefoams Inc.
55 Precision Drive
Walton KY, 41094 USA
Tel: +1 859 371 4025
Free: (800) 362-8358-4025
(US Only)

If you would like more information
email: hello@zotefoams.com
or visit our website
www.zotefoams.com

AZOTE® / **ZOTEK®** / **ECOZOTE®** / **T-FIT®**

